

FAST SETTING CONCRETE MIX

PRODUCT No. 1004-50

PRODUCT USE

QUIKRETE Fast Setting Concrete Mix is a general purpose concrete designed to achieve final set in 20-40 minutes. Fast Setting Concrete Mix is suitable for setting posts and pouring slabs when a rapid return to service is desired.

SIZES

• QUIKRETE Fast Setting Concrete Mix - 50 lb (22.7 kg) bags

YIELD

• Each 50 lb (22.7 kg) bag of QUIKRETE Fast Setting Concrete Mix will yield approximately 0.375 cu ft (11 L) of mixed concrete.
 • Two 50 lb (22.7 kg) bags of QUIKRETE Fast Setting Concrete Mix will set a 4" (102 mm) diameter post in a 10" (254 mm) diameter hole 2' (0.6 m) deep.

TECHNICAL DATA

APPLICABLE STANDARDS

ASTM International

- ASTM C39 Standard Test Method for Compressive Strength of Cylindrical Concrete Specimens
- ASTM C191 Standard Test Method for Time of Setting of Hydraulic Cement by Vicat Needle
- ASTM C387 Standard Specification for Packaged, Dry, Combined Materials for Mortar and Concrete

PHYSICAL/CHEMICAL PROPERTIES

Fast-Setting Concrete meets or exceeds the compressive strength requirements of ASTM C387. When mixed to a 2" - 3" (51 - 75 mm) slump, QUIKRETE Fast-Setting Concrete will achieve the typical physical properties shown in Table 1.

TABLE 1 TYPICAL PHYSICAL PROPERTIES

<u>Property & test</u>	<u>Results</u>
Setting time, ASTM C191	20 - 40 min.
Compressive strength, ASTM C39	2 hrs 400 psi (2.8 MPa)
	24 hrs 1000 psi (6.9 MPa)
	7 days 2500 psi (17.2 MPa)
	28 days 4000 psi (27.6 MPa)

INSTALLATION

FOR SETTING POSTS

1. Place post into hole and temporarily stand straight. The hole diameter should be 3 times the post diameter. The depth of the post hole should be one-half of the above ground post height.
2. Pour dry mix into the hole until it is approximately 3" - 4" (76 - 102 mm) from the top.
3. Pour water into the dry mix until the powder is saturated with water. Depending on soil conditions, this will require about 1 gallon (3.8 L) of water per 50 lb (22.7 kg) bag. For holes deeper than 2' 6" (0.8 m), place the material in lifts of 2' 6" (0.8 m) or less to allow water to soak all the way through.
4. Fill the remainder of the hole with soil dug from the hole. This product sets in 20 - 40 minutes. Wait 4 hours before placing heavy objects.

FOR POURING SLABS

MACHINE MIXING INSTRUCTIONS



APPLICATION

- Shovel or place concrete into form. Fill to the full depth of the form. Start in a corner and do not drag or flow the concrete unnecessarily
- After the concrete has been spread to completely fill the forms, strike off and float immediately
- To strike off, simply use a straight board, moving the edge back and forth with a saw-like motion to smooth the surface. Then use a darby or bull float to float the surface. This helps level any ridges and fills voids left by the straight edge
- Allow the concrete to stiffen slightly, waiting until all water has evaporated from the surface before troweling or applying a broom finish

Note - For best results, do not overwork the material. QUIKRETE Fast-Setting Concrete can be walked on in 2 hours. Wait at least 4 hours before placing heavy objects on the slab.

CURING

GENERAL

Curing is one of the most important steps in concrete construction. Proper curing increases the strength and durability of concrete. Proper water content and temperature are essential for good curing. In near freezing temperatures, the hydration process slows considerably. When weather is too hot, dry or windy, water is lost by evaporation from the concrete and hydration stops, resulting in finishing difficulties and cracks. The ideal circumstances for curing are ample moisture and moderate temperature and wind conditions.

SPECIFIC METHODS

Because QUIKRETE Fast-Setting Concrete is often used a few hours after placement, initial curing is very important. The most convenient curing method is to cover the concrete with plastic.

PRECAUTIONS

- Mix only as much material as can be placed in 20 minutes.
- Because of the rapid setting time, special precautions must be taken, as set times will fluctuate in extremely hot or cold weather. Use cold water or water mixed with ice cubes in severely hot weather. Use hot water when mixing in severely cold weather.

WARRANTY

The QUIKRETE® Companies warrant this product to be of merchantable quality when used or applied in accordance with the instructions herein. The product is not warranted as suitable for any purpose or use other than the general purpose for which it is intended. Liability under this warranty is limited to the replacement of

